

GUARDIAN

PRODUCT PROPERTIES

FIBER: Polypropylene
CONSTRUCTION: Spunbond
BONDING: Pointbond

FSP #	Weight (O.S.Y.)	Thick (mils)	Mullen Burst (PSI) ASTM D3786	Tensile Strength (ft/lbs) ASTM D5034		Perm (CFM) ASTM D737-75
				Machine Direct	Cross Direct	
SPB10	0.5	7	22	11	7	703
SPB16	0.8	9	31	18	11	455
SPB20	1.0	11	40	23	17	353
SPB25	1.25	13	43	30	22	253
SPB30	1.5	15	54	34	24	210
SPB40	2.0	17	62	48	37	133
SPB50	2.5	20	73	62	48	128
SPB60	3.0	25	76	60	52	145



Filtration Systems Products, Inc.

Fischer-Robertson, Inc.
3890 Symmes Road
Hamilton, OH 45015
ph 513-860-3445 fx 513-860-4744
www.fischer-robertson.com

This information is provided only as a general guide as to the likely properties of the product and neither FSP nor any of its divisions assumes any responsibility or liability whatsoever for the accuracy or completeness of the information contained herein nor do we undertake to notify any recipient of any changes of this information. The final determination of the suitability of this product for any application and whether its use in any application constitutes an infringement of any part or other intellectual property right is the sole responsibility of the user. Users of the product should satisfy themselves by independent investigation that it can be used safely to meet any specific functional requirements for any desired application.