

HOLLIFLO

PRODUCT PROPERTIES

FIBER: Polyester/Polypropylene
CONSTRUCTION: Needlepunch
BONDING: Proprietary

FSP #	Weight (O.S.Y.)	Thick (mils)	Mullen Burst (PSI) ASTM D3786	Tensile Strength (ft/lbs) ASTM D5034		Perm (CFM) ASTM D737-75
				Machine Direct	Cross Direct	
SHF50G	2.50	52	35	16	18	595
SHF60G	3.00	60	40	24	33	527
SHF8015	4.00	62	80	45	40	216
SHF80C	4.00	70	40	30	35	437
SHF100F	5.00	81	50	36	60	352



Filtration Systems Products, Inc.

Fischer-Robertson, Inc.
3890 Symmes Road
Hamilton, OH 45015
ph 513-860-3445 fx 513-860-4744
www.fischer-robertson.com

This information is provided only as a general guide as to the likely properties of the product and neither FSP nor any of its divisions assumes any responsibility or liability whatsoever for the accuracy or completeness of the information contained herein nor do we undertake to notify any recipient of any changes of this information. The final determination of the suitability of this product for any application and whether its use in any application constitutes an infringement of any part or other intellectual property right is the sole responsibility of the user. Users of the product should satisfy themselves by independent investigation that it can be used safely to meet any specific functional requirements for any desired application.

Revision B: 9/23/2015